ASTM G21-15(2021)

Standard Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi

FINAL REPORT: R2021-521

Prepared for:

Mermet

5970 N Main St

Cowpens, SC 29330

Accredited Testing Provided by:



130 Erick Street Crystal Lake, IL 60014 815.526.0954

TESTING CERT: #2832.01

Testing Initiated: August 12, 2021 Testing Completed: September 9, 2021 Report Issued: September 13, 2021

Performed By: Melissa Nolte

Title: Staff Scientist

Approved By: Debbie Koester Title: Quality Manager



Objective:

To evaluate the mold resistance properties of one sample as seen in the ASTM G21 fungal resistance test.

Test Sample Identification:

1. PVC Coated Fiberglass

Test Procedure Summary:

Samples are placed onto the surface of ASTM G21 nutrient salts agar and sprayed with a mixed spore suspension of five fungal strains. The nutrient salts agar provides all of the trace nutritional elements needed by fungi to support growth. However, to achieve a heavy growth, the fungi must use the test material as its primary carbon source. Inoculated samples are incubated and then examined for fungal growth.

Test Variables

Test Organisms:	Aspergillus brasiliensis¹ Talaromyces pinophilus ² Chaetomium globosum Trichoderma virens³ Aureobasidium pullulans	ATCC 9642 ATCC 11797 ATCC 6205 ATCC 9645 ATCC 15233			
Sample Description:	2" x 2" white woven pieces				
Number of Replicates per Sample:	Three				
Positive Growth Control:	Sterile Filter Paper				
Media Used:	Nutrient-Salts Agar prepared according to standard				
Environmental Conditions:	28 - 30°C; ≥85% relative humidity				
Incubation Duration:	28 days				
Deviations from	None, testing performed per ASTM G21 without				
Standard Test Method:	deviation.				

¹ Aspergillus brasiliensis formerly classified as Aspergillus niger

² Talaromyces pinophilus formerly identified as Penicillium funiculosum

³ Trichoderma virens formerly classified as Gliocladium virens




Results:

The results for the test pieces can be found in the data table below. The filter paper control pieces had copious fungal growth at Day 14. Temperature and relative humidity were maintained for the duration of the test. These results pertain only to the samples tested.

The rating scale for this test is as follows:

Rating	Observed Growth				
0	No Growth				
1	Trace of Growth (less than 10% coverage)				
2	Light Growth (10-30% coverage)				
3	Medium Growth (30-60% coverage)				
4	Heavy Growth (60-100% coverage)				

Sample Identification	Rep	Week 1	Week 2	Week 3	Week 4
PVC Coated Fiberglass	1	0	1	1	2
	2	0	1	1	2
	3	0	1	1	2



All replicates had light fungal growth.