



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 4, 2019

Mr. Nathan Wintermute
MERMET
5970 N. Main Street
Cowpens, SC 29330

Reference: Laboratory Test Report
Lab Identification No. 35274
Invoice No. 66484

Dear Mr. Wintermute:

One (1) sample, identified as **T SCREEN™ 3% WITH KOOLBLACK® TECHNOLOGY**, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. The results are as follows:

Test Results

<u>Specimen Number</u>	<u>After Flame (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	4.4	3.9
2	0.0	0.0	4.0	4.1
3	0.0	0.0	3.7	4.0
4	0.0	0.0	4.5	4.1
5	<u>0.0</u>	<u>0.0</u>	4.2	3.6
Avg.	0.0	0.0		

The fabric sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

